




Características Técnicas / Technical Features

TACOMA SILVER | SAND

Porcelanato masa coloreada

PHYSICAL PROPERTIES	NORM	REQUIREMENTS	MEAN VALUE ACHIEVED	
WATER ABSORPTION [%]	PN-EN-ISO 10545-3	<0,5	<0,1	
MODULUS OF RUPTURE [N/MM2]	PN-EN-ISO 10545-4	≥35	≥ 45	
BREAKING STRENGTH [N]	PN-EN-ISO 10545-4	>1300	>2100	
FROST RESISTANCE	PN-EN-ISO 10545-12	REQUIRED	RESISTANT SILVER 4/6000	
ABRASION RESISTANCE	PN-EN-ISO 10545-7	REQUIRED		
RESISTANCE TO HOUSEHOLD CHEMICALS	PN-EN-ISO 10545-13	MIN. B	AMMONIUM CHLORIDE SOLUTION	A
			SODIUM HYPOCHLORITE SOLUTION	A
RESISTANCE TO HIGH OR LOW CONCENTRATION OF ACIDS OR ALKALIS	PN-EN-ISO 10545-13	DECLARED	HYDROCHLORIC ACID SOLUTION, 3%	
			CITRIC ACID SOLUTION 100G/L	
			POTASSIUM HYDROXIDE SOLUTION, 30G/L	
			HYDROCHLORIC ACID, SOLUTION, 18%	
			LACTIC ACID SOLUTION, 5%	
RESISTANCE TO STAINING	PN-EN-ISO 10545-14	MIN. 3	5	
CRAZING RESISTANCE	PN-EN-ISO 10545-11	REQUIRED	RESITANT	
NON-SLIP QUALITIES	DIN 51130	-	R10	
THERMAL SHOCK RESISTANCE	PN-EN-ISO 10545-9	REQUIRED	RESISTANT	



ventas@gante.mx

gante.mx

INSPECCIONADO POR: Guandong Qingyuan.
Supervision Testing Institute of Quality and Metrology.

La información descrita representa los resultados del material sometido a pruebas. Prohibida su reproducción total o parcial sin la validación de laboratorio.

GANTE

Gral. Pablo A. Gonzalez Garza
No. 500, Col. San Jerónimo
Monterrey N.L. México
CP. 64640